

Thermal paste

Paste 8702 (ex PA 20)

-
- **silicone- and solvent-free heat-conducting paste**
 - **1 component**
 - **CMR-free ***
 - **high-performance and electrically insulating**
 - **excellent thermal conductivity**
 - **no metallic fillers**
 - **high-long-term stability**
 - **good creeping properties**
 - **ideal for different cooling applications, improves the heat-transfer**

* not subject to CMR labelling according to section 2 of the safety data sheet

Product specification:

Type:	Non-curing and non-drying paste	
Viscosity (23 °C):	Paste 8702	150'000 – 200'000 mPa·s
Density (22 °C):	Paste 8702	2.20 – 2.50 g/cm ³
Colour:	Nature (cream)	
Shelf life:	12 months in sealed original containers when stored in dry conditions (15°C to 25°C).	

Physical properties:

Thermal conductivity:	2.0 – 2.3 W/(m·K) (22 °C) 2.0 – 2.3 W/(m·K) (60 °C optional)	DIN EN ISO 22007
Thermal resistance:	No blooming after 4 h at 200 °C	
Operating temperature:	-60 °C up to +200 °C	

Electrical properties:

Dielectric strength:	25 kV/mm	IEC 60243-1, VDE 0303, TI.2
Volume resistance:	$10^{16} \Omega \cdot \text{cm}$ (23 °C/ 50 % r.F.)	IEC 60243-1, VDE0303, TI.30

Our technical advice, whether verbal, in writing or by way of trials - is given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. It does not release you from the obligation to test the products supplied by us to their suitability for the intended processes and uses. The application, use and processing of the products are beyond our control and therefore, entirely your own responsibility. Should in spite of this, liability be established by us and used by you. We will, of course, provide products of consistent quality within the scope of our General Conditions of Sale and Delivery.

TDS_8702_e/OT/12.08.2024